

Product Terratek® GDH-B1FA

Product Description Proprietary blend of natural and synthetic biodegradable polyesters suitable for injection molding and sheet extrusion. It also works well as an impact modifier for PLA given its elastomeric properties.

Renewable Content

Biobased content (ASTM D6866)	16%
Biomass content (by weight)	35%

Property	Test Method	Value
Specific Gravity	ASTM D792	1.23
Shrinkage (48 hrs- parallel direction)	ASTM D955	0.005 in/in
Shrinkage (48 hrs- perpendicular direction)	ASTM D955	0.001 in/in
Melt Index (190°C / 2.16 kg)	ASTM D1238	29 g/10 min
Tensile Strength (at Max)	ASTM D638	1,363.4 psi
Tensile Modulus	ASTM D638	638.2 psi
Elongation (at Break)	ASTM D638	>600%
Tear Strength	ISO 34-1	57 N/mm
Compress Set (22 hrs @ 23°C)	ISO 815/ASTM D395(B)	33%
Compress Set (22 hrs @ 70°C)	ISO 815/ASTM D395(B)	82%
Hardness (Shore A)	ASTM D2240	A74

Drying Conditions

Moisture level: at or below 0.04% (400 ppm)
 Method: Karl Fischer; if using a loss in weight analyzer, contact Green Dot for more information.
 Drying conditions: Desiccant dryer 140°F for 2 to 4 hours or until the recommended moisture level is reached

ATTENTION: Moisture in Terratek® FX resins may result in hydrolysis which can cause brittleness, loss in strength, and reduction in melt strength, in addition to potentially impacting the shelf life of finished parts and films.

Packaging and Storing

This resin is typically packaged in a sealed plastic or foil lined box, drum, or gaylord. The product should be stored in a cool, dry, and sanitary area to achieve maximum stability.

Processing Recommendations

Terratek® resins can be processed on conventional plastics equipment. Follow standard purging process with a polyolefin or purge compound, such as Dyna-Purge, etc. Melt temperature of the resin should remain below 350°F.

Extrusion Recommendations

Feed Zone	270°F to 300°F
Middle Zones	290°F to 320°F
Front Zones	300°F to 330°F
Die Zones	300°F to 330°F
Chill Rolls	40°F to 80°F

Molding Recommendations

Feed Zone	250°F to 300°F
Middle Zones	290°F to 320°F
Front Zones	300°F to 340°F
Nozzle/Die	300°F to 340°F
Mold	40°F to 80°F

The information and recommendations in this sheet are based on our experience and analysis using standard procedures, and are believed to be accurate and reliable. However, they serve merely as typical guides, and are presented in good faith for the benefit of our customers. No guarantee, expressed or implied, is made regarding accuracy of the analysis, patent infringement, liabilities, or risks involved from the application