

Product Terratek® BD4802

Product Description Proprietary blend of natural and synthetic biodegradable polyesters suitable for extrusion blow molding, sheet extrusion and thermoforming. This resin is made from polymers which pass industry standards for industrial composting.

Renewable Content	
Biobased content (ASTM D6866)	60%
Biomass content (by weight)	60%

Preliminary Data – Pending Third Party Analysis

Property	Test Method	Value
Melt Index (190°C / 2.16 kg)	ASTM D1238	1 g/10 min
Tensile Strength	ASTM D638	6,000 psi
Tensile Modulus	ASTM D638	400,000 psi
Elongation	ASTM D638	10.0%

Drying Conditions

Moisture level: at or below 0.04% (400 ppm)
 Method: Karl Fischer; if using a loss in weight analyzer, contact Green Dot for more information.
 Drying conditions: Desiccant dryer 140°F for 2 to 4 hours or until the recommended moisture level is reached

ATTENTION: Moisture in Terratek® resins may result in hydrolysis which can cause brittleness, loss in strength, and reduction in melt strength, in addition to potentially impacting the shelf life of finished parts.

Packaging and Storing

This resin is typically packaged in a sealed plastic or foil lined box, drum, or gaylord. The product should be stored in a cool, dry, and sanitary area to achieve maximum stability.

Processing Recommendations

Terratek® resins can be processed on conventional equipment. Follow standard purging process with a polyolefin or purge compound, such as Dyna-Purge, etc. Melt temperature of the resin should remain below 400°F.

Feed Zone	310°F to 320°F
Middle Zones	310°F to 320°F
Front Zones	300°F to 320°F
Die	300°F to 320°F

The information and recommendations in this sheet are based on our experience and analysis using standard procedures, and are believed to be accurate and reliable. However, they serve merely as typical guides, and are presented in good faith for the benefit of our customers. No guarantee, expressed or implied, is made regarding accuracy of the analysis, patent infringement, liabilities, or risks involved from the application